

TEST ITEM		UNIT	ASTM TEST	TYPICAL VALUES		
THICKNESS厚度				88um	100um	220um (试样)
<b>拉伸性能</b>						
拉力	MD	N/50mm	GB/T35467-2017		290	580
	TD				300	540
最大拉力延伸率	MD	%	GB/T35467-2017		320	280
	TD				330	300
<b>耐撕裂性能</b>						
撕裂强度	MD	N			38	
	TD				41	76
钉杆撕裂强度	MD	N	GB/T328.18-2007		140	230
	TD				142	220
<b>热老化性能</b>						
拉力保持率(80°C,168h)	MD	%	GB/T35467-2017		95	
	TD				99	
延伸率保持率(80°C,168h)	MD	%	GB/T35467-2017		96	
	TD				98	
低温柔性(-18°C)			GB/T35467-2017		无裂纹	
<b>尺寸稳定性</b>						
尺寸变化率(90°C,24h)	MD	%	GB/T35467-2017		1	0.9
	TD				0.8	0.7
<b>热稳定性</b>						
热稳定性(70°C,24h)	MD	%	GB/T35467-2017		≤15%	
	TD				≤15%	
<b>热收缩性能</b>				<b>MD</b>	<b>TD</b>	
热收缩率(120°C)	100°C	%	D2372	0.8	0	
	110°C			1.2	0.5	
	120°C			2	1	
	130°C					
<b>其它</b>						
水汽透过率				waterproof不透水		
工作温度				-50°C~+90°C		

以上资料是本公司内部评测之数据，仅供参考。

Note: This information represents our best judgment on the work done. But the company assumes no liability whatsoever in connection with the use of information or findings contained herein.